

## DUPLI-COLOR profi Multi Primer

## Technical Information



Suited as all-purpose primer on iron, steel, zinc, aluminium, anodized aluminium, V2A steel, powder-coated components, different plastics and wood. Active corrosion protection with exceptional adhesion, heat resistance and high filling.

Ord.-no: 478352, 478369

### Quality & properties

Based on synthetic resins  
Weather resistant  
Quick drying  
Very good adhesion  
Heat resistant up to 80°C dry heat  
Nitro thinner resistant (after through drying)

### Physical & chemical data

Base: Special resin  
Colourname:  
◦ grey  
◦ white  
Degree of gloss: mat GU  
Efficiency: 400 ML – 1.5 - 2.0 m²  
Dry to touch: 60 min  
Dust dry: 40 min  
Overcoatable: 3-4 h  
Surfaces: plastics and wood  
Minimum Working Temperature: 10 °C  
Maximum Working Temperature: 25 °C  
Storage stability: 10 y  
Content: 400 ML

### How to use

Clean surfaces to be painted thoroughly with DUPLI-COLOR Degreaser art.no. 478376, then sand  
The area must be dry and free of dust and grease  
Always remove loose rust and mill scale.  
Sanding  
Shake can well for 3 minutes  
Carry out spray test  
2-3 coats  
Wear an appropriate respirator (type A2/P3)

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

**As of May 21, 2025** – This release replaces all eventually earlier issued versions.