

DUPLI-COLOR STRUCTURE SPRAY**Technical Information**

High-grade special lacquer with rough surface for individual styling of car parts or also for do-it-yourselfers. For decorative and hobbyists' works on metal, wood, glass, stone, ceramics, cardboard and many hard plastics.

Ord.-no: 693687, 695995, 693656

Quality & properties

High-grade nitro-combi quality
Special, rough texture
Satin gloss
Very good coverage
Excellent adhesion
Quick-drying
Suitable for painting and repair of indoors and outdoors objects
Excellent colour retention: weather-resistant, light-proof, UV-resistant
Excellently re-coatable

Physical & chemical data

Base: Special resin
Colourname:

- anthracite
- black
- silver

Degree of gloss: satin mat GU
Efficiency: 400 ML – 1.5 m²
Dry to touch: 50 min
Dust dry: 10 min
Overcoatable: 3 h
Surfaces: metal, wood, glass, stone, ceramics, cardboards and coatable hard plastics
Minimum Working Temperature: 10 °C
Maximum Working Temperature: 25 °C
Flash point: n.a.
Storage stability: 10 y
Content: 400 ML

How to use

Clean underground from dirt and fat.

Derust metals.

On plastic parts always use DUPLI-COLOR PLASTIC PRIMER; on other surfaces use DUPLI-COLOR PRIMER or UNIVERSAL PRIMER.

Fill and sand uneven surfaces. Before that, generously mask off the repair spot. Larger surfaces should be masked off at creases and edges of the car body, too.

The surface has to be clean, dry and free from fat.

Before use, shake the can vigorously for 3 minutes.

Test spray to check colour-matching and compatibility.

Spray from a distance of approx. 25 cm several thin coats in 3 -5 minute intervals.

Earliest after 3 hours drying time it is possible to apply any DUPLI-COLOR top coat. Depending on thickness of the applied coat, the intensity of the achieved structure can degrease.

Do not spray over synthetic paints!

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 21, 2025 – This release replaces all eventually earlier issued versions.